

MOSAIC REVOLUTION
patent pending

TESTS

Result of the tests					
Test	Standard	Performing test	Result		
Resistance to light	UNIEN 15187:2007	EXPOSURE FOR 20 HOURS	no change		
Resistance to temperature	UNI 9429:1989	Exposure Cycle: 4h-20° C 4h + 50° C - 16h + 23° C	after 15 cycles no defects		
Cycles of heat and humidity	PTP 45:1995	Exposure for 72 hours in a climatic chamber temperature +45° and humidity 95%	after the test no defects		
Resistance to cleaning products	PTP 53:1995	Contact time of 6 hours			
Product tested		Ajax floors	after the test no defects		
		Denatured alcohol	after the test no defects		
		Ammonia (sol. 6/7%)	after the test no defects		
		Bleach Ace	after the test no defects		
		Cif Gel with bleach	after the test no defects		
		Cif Active Spray with Bleach	after the test no defects		
Product tested		Mastro Lindo	after the test no defects		
		Surface resistance to cold liquids	EN 12720:2009	contact time of 16 hours	
		Product tested		Acetone	modified structure of the surface
				Acetic acid (aqueous solution 10%)	modified structure of the surface
				Citric acid (aqueous solution 10%)	modified structure of the surface
				Distilled water	no damage
Ammonia (10% aqueous solution)	no damage				
Beer	no damage				
Coffe	no damage				
Sodium carbonate (10% aqueous solution)	no damage				
Chloramine T (solution Aqueous 2,5%)	no damage				
Sodium chloride	no damage				
Ethanol (solution Aqueous 48%)	no damage				
Ethyl-butyl acetate (1:1)	modified structure of the surface				
Ink for stamps	sign pronounced				
Olive oil	no damage				
Paraffin oil	no damage				
Cleaning solution	no damage				
Tea	no damage				
Red wine	no damage				
Not suitable for walking					